



## Technical Data Sheet

**Product : CC 280**

Fiber	Warp	Toray 3K 200 tex
	Weft	Toray 3K 200 tex
Area weight	280 g/m <sup>2</sup> ± 3%	
Binding	Twill 2/2, Twill 4/4	
Width	100 cm	
Sett of (per 1 cm)	Warp	7
	Weft	7
Compatibility	Epoxy, phenolic	
Standard packing	70 m	

ISO 9001 : 2015  
ISO 14001 : 2015



Kordcarbon a.s., 696 74 Velká nad Veličkou 890, Czech Republic  
email : [info@kordcarbon.com](mailto:info@kordcarbon.com), [www.kordcarbon.com](http://www.kordcarbon.com)