



## Technical Data Sheet

### Product : CK 190

Fiber	Warp	Toray 3K 200 tex Kevlar 127 tex (1:1)
	Weft	Toray 3K 200 tex Kevlar 127 tex (1:1)
Area weight	190 g/m <sup>2</sup> ± 3%	
Binding	Twill 2/2	
Width	100, 120 cm	
Sett of (per 1 cm)	Warp	5,8
	Weft	5,8
Compatibility	Epoxy resin	
Standard packing	100 m	

ISO 9001 : 2015  
ISO 14001 : 2015



Kordcarbon a.s., 696 74 Velká nad Veličkou 890, Czech Republic  
email : [info@kordcarbon.com](mailto:info@kordcarbon.com), [www.kordcarbon.com](http://www.kordcarbon.com)